

This Page Is Inserted by IFW Operations
and is not a part of the Official Record

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images may include (but are not limited to):

- BLACK BORDERS
- TEXT CUT OFF AT TOP, BOTTOM OR SIDES
- FADED TEXT
- ILLEGIBLE TEXT
- SKEWED/SLANTED IMAGES
- COLORED PHOTOS
- BLACK OR VERY BLACK AND WHITE DARK PHOTOS
- GRAY SCALE DOCUMENTS

IMAGES ARE BEST AVAILABLE COPY.

**As rescanning documents *will not* correct images,
please do not report the images to the
Image Problem Mailbox.**


THIS PAGE BLANK (USPTO)



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<p>(51) International Patent Classification ⁷ : H01L 33/00</p>	<p>A1</p>	<p>(11) International Publication Number: WO 00/08691</p> <p>(43) International Publication Date: 17 February 2000 (17.02.00)</p>
<p>(21) International Application Number: PCT/US99/17486</p> <p>(22) International Filing Date: 2 August 1999 (02.08.99)</p> <p>(30) Priority Data: 09/128,516 3 August 1998 (03.08.98) US Not furnished 30 July 1999 (30.07.99) US</p> <p>(71) Applicant: THE CURATORS OF THE UNIVERSITY OF MISSOURI [US/US]; 509 Lewis Hall, Columbia, MO 65211 (US).</p> <p>(72) Inventors: WHITE, Henry, W.; 601 Maplewood Drive, Columbia, MO 65211 (US). ZHU, Shen; Apartment 47, 2500 Redstone Road, Huntsville, AL 35803 (US). RYU, Yungryel; Apartment 2, 1708 Kitty Hawk, Columbia, MO 65202 (US).</p> <p>(74) Agents: HEJLEK, Edward, J. et al.; Senniger, Powers, Leavitt & Roedel, 16th Floor, One Metropolitan Square, St. Louis, MO 63102 (US).</p>		<p>(81) Designated States: AU, BR, CA, CN, IN, JP, RU, European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE).</p> <p>Published <i>With international search report. Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i></p>

(54) Title: ZINC OXIDE FILMS CONTAINING P-TYPE DOPANT AND PROCESS FOR PREPARING SAME



(57) Abstract

A p-type zinc oxide film and a process for preparing the film and p-n or n-p junctions is disclosed. In a preferred embodiment, the p-type zinc oxide film contains arsenic and is grown on a gallium arsenide substrate. The p-type zinc oxide film has a net acceptor concentration of at least about 10^{15} acceptors/cm³, a resistivity of no greater than about 1 ohm-cm, and a Hall mobility of between about 0.1 and about 50 cm²/Vs.

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

ZINC OXIDE FILMS CONTAINING P-TYPE
DOPANT AND PROCESS FOR PREPARING SAME

BACKGROUND OF THE INVENTION

5 This invention is directed to zinc oxide (ZnO) films for use in electrically excited devices such as light emitting devices (LEDs), laser diodes (LDs), field effect transistors (FETs), and photodetectors. More particularly, this invention is directed to ZnO films containing a p-type
10 dopant for use in LEDs, LDs, FETs, and photodetectors wherein both n-type and p-type materials are required, for use as a substrate material for lattice matching to other materials in such devices, and for use as a layer for attaching electrical leads.

15 For some time there has been interest in producing II-VI compound wide band gap semiconductors to produce green/blue LEDs, LDs and other electrical devices. Historically, attempts to produce these devices have centered around zinc selenide (ZnSe) or gallium nitride
20 (GaN) based technologies. However, these approaches have not been entirely satisfactory due to the short lifetime of light emission that results from defects, and defect migration, in these devices.

 Recently, because ZnO has a wide direct band gap of
25 3.3 eV at room temperature and provides a strong emission source of ultraviolet light, ZnO thin films on suitable supporting substrates have been proposed as new materials for light emitting devices and laser diodes. Undoped, as well as doped ZnO films generally show n-type conduction.
30 Impurities such as aluminum and gallium in ZnO films have been studied by Hiramatsu et al. who report activity as n-type donors (Transparent Conduction Zinc Oxide Thin Films

Prepared by XeCl Excimer Laser Ablation, J. Vac. Sci. Technol. A 16(2), Mar/Apr 1998). Although n-type ZnO films have been available for some time, the growth of p-type ZnO films necessary to build many electrical devices requiring p-n junctions has to date been much slower in developing.

5 Minegishi et al. (Growth of P-Type ZnO Films by Chemical Vapor Deposition, Jpn. J. Appl. Phys. Vol. 36 Pt. 2, No. 11A (1997)) recently reported on the growth of nitrogen doped ZnO films by chemical vapor deposition and on the p-type conduction of ZnO films at room temperature. Minegishi et al. disclose the growth of p-type ZnO films on a sapphire substrate by the simultaneous addition of NH₃ in carrier hydrogen and excess Zn in source ZnO powder. When a Zn/ZnO ratio of 10 mol% was used, secondary ion mass spectrometry (SIMS) confirmed the incorporation of nitrogen into the ZnO film, although the nitrogen concentration was not precisely confirmed. Although the films prepared by Minegishi et al. using a Zn/ZnO ratio of 10 mol% appear to incorporate a small amount of nitrogen into the ZnO film and convert the conduction to p-type, the resistivity of these films is too high for application in commercial devices such as LEDs or LDs. Also, Minegishi et al. report that the carrier density for the holes is 1.5×10^{16} holes/cm³. The combined effect of the low carrier density for holes and the high value for the resistivity does not permit this material to be used in commercial light emitting devices or laser diodes.

20 Park et al. in U.S. Patent No. 5,574,296 disclose a method of producing thin films on substrates by doping IIB-VIA semiconductors with group VA free radicals for use in electromagnetic radiation transducers. Specifically, Park et al. describe ZnSe epitaxial thin films doped with

nitrogen or oxygen wherein ZnSe thin layers are grown on a GaAs substrate by molecular beam epitaxy. The doping of nitrogen or oxygen is accomplished through the use of free radical source which is incorporated into the molecular beam epitaxy system. Using nitrogen as the p-type dopant, net acceptor densities up to 4.9×10^{17} acceptors/cm³ and resistivities less than 15 ohm-cm were measured in the ZnSe film. The combined effect of the low value for the net acceptor density and the high value for the resistivity does not permit this material to be used in commercial devices such as LEDs, LDs, and FETs.

Although some progress has recently been made in the fabrication of p-type doped ZnO films which can be utilized in the formation of p-n junctions, a need still exists in the industry for ZnO films which contain higher net acceptor concentrations and possess lower resistivity values.

SUMMARY OF THE INVENTION

Among the objects of the present invention, therefore, are the provision of a ZnO film containing a high net acceptor concentration on a substrate; the provision of a process for producing ZnO films containing p-type dopants; the provision of a process for producing p-n junctions utilizing a ZnO film containing a p-type dopant; the provision of a process for producing homoepitaxial and heteroepitaxial p-n junctions utilizing a ZnO film containing a p-type dopant; and the provision of a process for cleaning a substrate prior to growing a film on the substrate.

Briefly, therefore, the present invention is directed to a ZnO film on a substrate wherein the film contains a p-

type dopant. The film has a net acceptor concentration of at least about 10^{15} acceptors/cm³, a resistivity less than about 1 ohm-cm, and a Hall Mobility of between about 0.1 and about 50 cm²/Vs.

5 The invention is further directed to a process for growing a p-type ZnO film containing arsenic on a GaAs substrate. The GaAs substrate is first cleaned to ensure that the film will have a reduced number of defects and will properly adhere to the substrate. After cleaning the
10 temperature in the chamber is adjusted to between about 300°C and about 450°C and the excimer pulsed laser is directed onto a polycrystalline ZnO crystal to grow a film on the substrate. The temperature of the deposition chamber containing the substrate coated with the film is
15 then increased to between about 450°C and about 600°C and the substrate is annealed for a time sufficient to diffuse arsenic atoms into the film so as to produce a net acceptor concentration of at least about 10^{15} acceptors/cm³ in the film.

20 The invention is further directed to a process for growing a p-type zinc oxide film on a substrate. The substrate is first cleaned to ensure that the film will have a reduced number of defects and will properly adhere to the substrate. After cleaning the substrate, the
25 temperature in the chamber is adjusted to between about 300°C and about 450°C, and a p-type zinc oxide film is grown on the substrate by directing an excimer pulsed laser beam onto a pressed ZnO powder pellet containing a p-type dopant to grow a p-type zinc oxide film containing a net acceptor
30 concentration of at least about 10^{15} acceptors/cm³.

 The invention is further directed to a process for preparing a p-n junction having a p-type ZnO film and an n-

type film wherein the net acceptor concentration is at least about 10^{15} acceptors/cm³. A substrate is loaded into a pulsed laser deposition chamber and cleaned to ensure that the film will have a reduced number of defects and will properly adhere to the substrate. The temperature in the deposition chamber is then raised to between about 300°C and about 450°C. Subsequently a p-type ZnO film having a net acceptor concentration of at least about 10^{15} acceptors/cm³ is grown on the substrate by directing an excimer laser onto a pressed ZnO powder pellet containing the p-type dopant. Finally an n-type film is grown on top of the p-type film by directing an excimer laser beam onto a pressed ZnO pellet containing the n-type dopant.

The invention is further directed to a process for preparing a p-n junction having a p-type ZnO film and an n-type film wherein the net acceptor concentration is at least about 10^{15} acceptors/cm³. A substrate is loaded into a pulsed laser deposition chamber and cleaned to ensure that the film will have a reduced number of defects and will properly adhere to the substrate. The temperature in the deposition chamber is then raised to between about 300°C and about 450°C. Subsequently an n-type film is grown on the substrate by directing an excimer pulsed laser beam onto a pressed powder pellet containing an n-type dopant element. Finally, a p-type ZnO film is grown on the n-type film by directing an excimer pulsed laser beam onto a pressed ZnO powder pellet containing a p-type dopant element to a p-type ZnO film having a net acceptor concentration of at least about 10^{15} acceptors/cm³.

The invention is further directed to a process for cleaning a substrate prior to growing a film on the substrate. A substrate is loaded into a chamber, the

temperature is adjusted to between about 400°C and about 500°C, and the chamber is filed with hydrogen to create a pressure between about 0.5 and about 3 Torr. The distance between a metal shutter in the chamber and the substrate is
5 adjusted to between about 3 and about 6 centimeters and an excimer pulsed laser having an intensity between about 20 and about 70 mJ and a repetition of between about 10 to about 30 Hz is directed onto the shutter for a period of between about 5 and about 30 minutes to clean the
10 substrate.

The invention is still further directed to a p-type film on a substrate wherein the film contains a p-type dopant element which is the same element as one constituent of the substrate.

15 The invention is further directed to a process for preparing a p-n junction having a p-type ZnO film and an n-type ZnO film on a p-type doped substrate wherein the net acceptor concentration is at least about 10^{15} acceptors/cm³. The process comprises adjusting the temperature in a pulsed
20 laser deposition chamber to between about 300 and about 450°C and growing a p-type ZnO film on the substrate by directing an excimer pulsed laser beam onto a pressed ZnO powder pellet containing a p-type dopant and growing an n-type film on top of the p-type film.

25 The invention is further directed to a process for growing a doped ZnO film on a substrate. The process comprises adjusting the temperature in a pulsed laser deposition chamber to between about 300 and about 450°C and pre-ablating a polycrystalline ZnO crystal. Finally, an
30 excimer pulsed laser beam is directed onto the polycrystalline ZnO crystal to grow a film on the GaAs substrate while a molecular beam containing a dopant is

simultaneously directed onto the growing ZnO film for a time sufficient to incorporate at least about 10^{15} dopant/cm³.

Other objects and features of this invention will be in part apparent and in part pointed out hereinafter.

BRIEF DESCRIPTION OF THE DRAWINGS

Fig. 1 is a schematic diagram of a pulsed laser deposition system.

Fig. 2 is a photoluminescence spectra at 20°K of a ZnO film and an arsenic-doped ZnO film prepared in accordance with the present invention.

Fig. 3 is a Secondary Ion Mass Spectroscopy (SIMS) plot of an arsenic doped ZnO film prepared in accordance with the present invention.

Fig. 4 is an Atomic Force Microscopy image of a ZnSe film on a GaAs substrate wherein the substrate was cleaned using the cleaning process of the present invention.

Fig. 5 is an Atomic Force Microscopy image of a ZnSe film on a GaAs substrate wherein the substrate was cleaned using a thermal process.

Fig. 6 is a table showing various electrical properties of an aluminum doped ZnO n-type film.

Fig. 7 is a current voltage measurement made on an aluminum doped ZnO -type film.

Fig. 8 is a current voltage measurement made on an arsenic doped ZnO p-type film.

Fig. 9 is a current voltage measurement made on a p-n junction.

Fig. 10 is a schematic diagram of a p-n junction.

Corresponding reference characters indicate corresponding parts throughout the drawings.

DETAILED DESCRIPTION OF THE PREFERRED EMBODIMENTS

In accordance with the present invention, it has been discovered that ZnO films containing high levels of p-type dopants can be grown on substrates utilizing a pulsed laser deposition process alone or in combination with an annealing step. Surprisingly, the p-type dopant level achieved in the ZnO film is sufficient to allow the p-type film to be used to form p-n junctions useful in electrical and electroluminescent devices, for use as a substrate material for lattice matching to materials in such devices, and for use as a desirable layer for attaching electrical leads.

Referring now to Fig. 1, there is shown a schematic diagram of a pulsed laser deposition system. Such a system is one method that can be utilized to grow ZnO films containing p-type dopants on suitable substrates. Other methods of growing ZnO films containing p-type dopants on substrates may include molecular beam epitaxy (MBE), MBE in conjunction with laser ablation, and chemical vapor deposition (CVD). Suitable p-type dopants for use in the present invention include Group 1 (also known as IA, which includes elements such as Li, Na, K, Rb, and Ca), Group 11 (also known as IB, which includes elements such as Cu, Ag, and Au), Group 5 (also known as VB, which includes elements such as V, Nb, and Ta), and Group 15 (also known as VA, which includes elements such as N, P, Sb, As, and Bi), with arsenic being preferred.

Again referring to Fig. 1, there is shown a focusing lens 8 capable of directing an excimer laser beam 10 through laser window 6 into pulsed laser deposition chamber 2. The beam 10 can be directed onto either metal shutter 4 or target 18 depending upon the desired processing step.

The beam 10 impinges on either metal shutter 4 or produces an ablation plume of ZnO material from the target 18 and onto substrate 12. During the process of growing ZnO films, gas inlet tube 14 allows gas 16 into the chamber 2.

5 Before growth of the ZnO film on the substrate, the substrate should be cleaned in order to remove surface contaminants such as oxygen and carbon to minimize the number of defects in the film and to ensure maximum adherence of the film to the substrate. Conventional
10 substrate cleaning techniques including wet chemical treatments, thermal cleaning, hydrogen atom plasma treatments, or any combination thereof can be used to sufficiently clean the substrate surface. In addition, a pulsed excimer laser, such as a pulsed argon fluoride
15 excimer laser, can be used to clean the substrate in situ.

To clean the substrate using a pulsed excimer laser, the temperature of the substrate in the pulsed laser deposition chamber 2 is first adjusted to between about 300°C and about 600°C, more preferably between about 400°C
20 and about 500°C, most preferably to about 450°C, and the chamber 2 is filled with a gas such as hydrogen to create a pressure of between about 0.5 and about 3 Torr, preferably between about 1 to about 2 Torr. Referring again to Fig. 1, a metal shutter 4, which may be made from
25 iron, for example, is inserted between the target 18 and the substrate 12 such that the substrate is positioned between about 3 and about 6 centimeters, preferably about 4 centimeters, in front of the metal shutter 4. The focusing lens 8 is removed from the system, and an excimer
30 laser beam 10, such as an argon fluoride excimer laser beam having an intensity of between about 20 and about 70 mJ, preferably about 50 mJ and a repetition rate of about 10 to

about 30 Hz, preferably about 20 Hz, is directed into the chamber 2 and onto the metal shutter 4 for a period of between about 5 and about 30 minutes, preferably about 10 minutes.

5 During this period of illumination of the metal shutter, the laser beam interacts with the metal shutter and creates excited hydrogen atoms, photoelectrons, and photons that effectively remove contaminants from the substrate surface. Using the pulsed excimer laser, the
10 substrate surface can be effectively cleaned at a much lower temperature than that required by conventional techniques. The pulsed excimer laser cleaning process can be effectively utilized to clean GaAs, GaN, sapphire, and other substrates prior to the deposition of ZnO, ZnSe, GaN
15 and other films. For example, Figs. 4 and 5 show Atomic Force Microscopy (AFM) images of the surface morphology of a ZnSe film on GaAs substrates. In Fig. 4, the GaAs substrate was cleaned prior to the deposition of the ZnSe film using the cleaning process described above. The
20 deposited ZnSe film has a thickness of about 0.5 micrometers and has only a root mean surface roughness of about 1.05 nanometers. In Fig. 5, the GaAs substrate was cleaned prior to the deposition of the ZnSe film by a thermal treatment process at a substrate temperature of
25 about 570°C. The deposited ZnSe film has a thickness of about 0.5 micrometers and has a root mean surface roughness of about 6.65 nanometers. As indicated in Figs. 4 and 5, the cleaning process of the present invention leaves a much improved uniform surface for subsequent film growth.

30 After the period of illumination is complete, the hydrogen gas is pumped out of chamber 2, and the temperature of the substrate is adjusted to between about

200°C and about 1000°C, preferably between about 250°C and about 500°C, and most preferably to between about 300°C and about 450°C, to grow the ZnO film.

After the substrate has been cleaned and the temperature in the chamber adjusted, the focusing lens 8 is replaced, the metal shutter 4 is removed and the target is pre-ablated with a pulsed excimer laser having an intensity of between about 20 and about 70 mJ, preferably about 50 mJ, and a repetition rate of between about 10 and about 30 Hz, preferably about 20 Hz for a period of about 10 minutes.

After the pre-ablation is complete, the chamber 2 is filled with oxygen to a pressure of between about 20 and about 40 mTorr, preferably about 35 mTorr. The laser beam 10 is directed through focusing lens 8 and laser window 6 onto the target 18 to produce an ablation plume of ZnO material that is adsorbed onto substrate 12. The target 18 is between about 5 and about 10 centimeters, preferably about 7 centimeters from the substrate 12. Suitable targets for use in the present invention include polycrystalline ZnO and ZnO powder pellets containing a dopant. Suitable substrates for use in the present invention include gallium arsenide, sapphire, and ZnO. The laser beam 10 can have an intensity of about 90 mJ and a repetition of about 20 Hz, for example. The laser beam 10 is directed at the target 18 for a period of about 0.5 to about 4 hours, preferably about 1 to about 2 hours to grow a ZnO film on substrate 12 between about 0.5 and about 3 micrometers thick, preferably about 1 micrometer thick.

In a particularly preferred embodiment of the present invention, the target 18 is polycrystalline ZnO, the substrate 12 is gallium arsenide, and the p-type dopant is

arsenic. If the growth of the ZnO film on the gallium arsenide substrate as described above occurred at a temperature of at least about 400°C, no further processing steps are necessary, and the ZnO layer will contain a net acceptor concentration of at least about 10^{15} acceptors/cm³, preferably at least about 10^{16} acceptors/cm³, more preferably at least about 10^{17} acceptors/cm³, and more preferably between about 10^{18} and about 10^{21} acceptors/cm³ as arsenic atoms will migrate from the gallium arsenide substrate into the ZnO film during the film growth at a temperature of at least about 400°C. Additionally, the film will have a resistivity of no more than about 1 ohm-cm, preferably between about 1 and about 10^{-4} ohm-cm, and a Hall mobility of between about 0.1 and about 50 cm²/Vs.

If the growth of the ZnO film on the gallium arsenide substrate occurs below about 400°C, a further processing step (annealing) is required to diffuse arsenic from the substrate into the ZnO film. This annealing step consists of adjusting the temperature of the substrate in the chamber 2 to between about 450°C and about 600°C, preferably to about 500°C, and filling the chamber 2 with a gas such as oxygen at a pressure between about 0.5 and about 4 Torr, preferably about 1 to about 2 Torr. The gallium arsenide substrate is annealed for a period of between about 10 and about 60 minutes, preferably about 20 to about 30 minutes to produce a net acceptor concentration of at least about 10^{15} acceptors/cm³, preferably at least about 10^{16} acceptors/cm³, more preferably at least about 10^{17} acceptors/cm³, and most preferably between about 10^{18} acceptors/cm³ and about 10^{21} acceptors/cm³ from the substrate into the ZnO film.

Without being bound to a particular theory, in the one preferred embodiment when arsenic dopant from a GaAs substrate is caused to diffuse into a ZnO film, superior results are achieved due in substantial part to the fact that the p-type dopant elemental source is the substrate itself. The p-type dopant elemental source is therefore in intimate contact with the film, which facilitates diffusion more efficiently and to a greater degree as compared to processes in which the substrate is not the dopant source.

In this particular embodiment, therefore, having the dopant source be the substrate facilitates achieving the improvements in net acceptor concentration, resistivity, and Hall mobility described herein. Also, the cleaning process as described herein utilized with the preferred film growing and annealing processes cleans the GaAs surface extremely well to remove contaminants such as carbon and oxygen without damaging the crystal structure. The clean, non-damaged surface allows the ZnO film to grow with improved crystal alignment and with a reduced number of defects. This cleaning process therefore further facilitates diffusion of arsenic more efficiently and to a greater degree, which results in improvements in structural, optical and electrical properties.

In an alternative embodiment, ZnO films containing p-type dopants such as arsenic or n-type dopants such as aluminum can be grown on substrates such as ZnO, GaAs, GaN and sapphire using a process wherein an excimer pulsed laser beam is directed onto a pressed ZnO powder pellet while simultaneously directing a molecular beam of arsenic or aluminum onto the growing ZnO film from either a thermal evaporation source or an arsenic or aluminum containing gas. The substrate is held at a temperature of between

about 200°C and about 1000°C, preferably between about 300°C and about 450°C and is filled with oxygen at a pressure of about 20 mTorr and about 40 mTorr. A pre-ablation step may be employed on the ZnO target as described above. The
5 combination of the required molecular beam flux and the length of time required for the molecular beam containing the dopant to be directed at the substrate is sufficient to achieve a net acceptor or donor concentration of at least about $10^{15}/\text{cm}^3$, more preferably at least about $10^{16}/\text{cm}^3$ still
10 more preferably at least about $10^{17}/\text{cm}^3$, and still more preferably between about $10^{18}/\text{cm}^3$ and about $10^{21}/\text{cm}^3$.

In a further alternative embodiment, ZnO films containing p-type dopants such as arsenic on a substrate can be prepared using pressed ZnO powder pellets containing
15 a p-type dopant as the target in the pulsed laser deposition chamber. This process does not require migration of the dopant from the substrate into the film.

A ZnO film is grown on a suitable substrate using the pulsed laser deposition method described above except that
20 the target is a pressed ZnO powder pellet that contains a small amount of elemental p-type dopant. The amount of dopant, such as arsenic, required in the powder pellet to achieve a net acceptor concentration level of at least about 10^{15} acceptors/ cm^3 , preferably at least about 10^{16}
25 acceptors/ cm^3 , more preferably at least about 10^{17} acceptors/ cm^3 , and still more preferably between about 10^{18} acceptors/ cm^3 and about 10^{21} acceptors/ cm^3 is determined by measuring the amount of dopant in the ZnO film and adjusting the dopant level in the powdered pellet until the
30 net acceptor concentration of at least about 10^{15} acceptors/ cm^3 , preferably at least about 10^{16} acceptors/ cm^3 , still more preferably at least about 10^{17} acceptors/ cm^3 and

most preferably between about 10^{16} acceptors/cm³ and about 10^{21} acceptors/cm³ is reached. For example, secondary ion mass spectroscopy (SIMS) can be used to determine the amount of dopant in the ZnO film. Additionally, Hall measurements in combination with electrical resistivity measurements can be used to determine whether the ZnO film is p-type or n-type, the net concentration of p-type or n-type carriers in the ZnO film, to determine the Hall mobility of the carriers, and to determine the electrical resistivity of the ZnO film. One skilled in the art will realize that the amount of dopant required in the powdered pellet may depend on numerous factors including operating conditions, distances from the target to the substrate, the size and shape of the chamber, as well as other variables during growth.

The concentration of p-type dopant may be varied within the p-type film by using more than one target and by selecting the target source during growth that yields the desired acceptor concentrations in the ZnO film. Such variations may be desirable in order to prepare surfaces onto which electrical leads may be attached that have desirable electrical properties.

Also in accordance with the present invention homoepitaxial and heteroepitaxial p-n junctions containing p-type doped ZnO films may be produced on suitable substrates such as gallium arsenide, sapphire and ZnO. It will be recognized by one skilled in the art that the terms "homoepitaxial" and "heteroepitaxial" are commonly used in the art interchangeably with "homosubstructural" and "heterosubstructural," respectively. The term "homosubstructural" is generally used when referring to structures wherein the materials have the same energy band

gap and "heterostructural" is generally used when referring to structures wherein the materials have different energy band gaps.

The substrates may be doped with a p-type dopant to provide electrical contact to a p-n junction formed on the substrate. It will be recognized by one skilled in the art that an undoped substrate could also be used to grow a p-n junction on the undoped substrate. If the substrate is doped with a p-type dopant, such as zinc, the p-type layer is deposited on the p-type substrate, and finally the n-type layer is deposited on the p-type layer. Similarly, if the substrate is n-type doped then the n-type layer is deposited first and then the p-type layer. Such configurations avoid any p-n junction formation between the substrate and the first deposited layer. The substrates are generally doped with a p or n type dopant to create at least about $10^{15}/\text{cm}^3$, more preferably at least about $10^{16}/\text{cm}^3$, still more preferably at least about $10^{17}/\text{cm}^3$ and most preferably between about 10^{18} and about $10^{21}/\text{cm}^3$. It will again be recognized by one skilled in the art that if an undoped substrate is used, either the p-type or n-type film can be first grown on the substrate.

To produce a homoepitaxial p-n junction, a p-type ZnO layer is first grown on the substrate utilizing a pressed ZnO powder pellet containing a p-type dopant such as arsenic as described above to obtain a net acceptor concentration of at least about 10^{15} acceptors/ cm^3 , more preferably at least about 10^{16} acceptors/ cm^3 , still more preferably at least about 10^{17} acceptors/ cm^3 , and most preferably between about 10^{18} acceptors/ cm^3 and about 10^{21} acceptors/ cm^3 . The concentration of p-type dopant may be varied across the p-type film by using more than one target

and by selecting the target source during growth that yields the desired acceptor carrier concentration in the ZnO film. Such variations may be desirable in order to prepare surfaces onto which electrical leads may be attached that have desirable electrical properties.

To complete the homoepitaxial p-n junction, an n-type ZnO film is grown on top of the p-type ZnO film on top of the substrate. The n-type ZnO film is grown on top of the p-type ZnO film utilizing a pressed ZnO powder pellet containing an n-type dopant such as aluminum, gallium, or indium as described above to yield an n-type film having a net donor concentration of at least about 10^{15} donors/cm³, more preferably at least about 10^{16} donors/cm³, more preferably at least about 10^{17} donors/cm³, and most preferably between about 10^{18} donors/cm³ and about 10^{21} donors/cm³. As with the p-type film, the concentration level of the n-type carriers may be varied across the film by employing more than one target.

A heteroepitaxial p-n junction can also be produced in accordance with the present invention. To prepare a heteroepitaxial p-n junction, a p-type ZnO film is grown on a suitable substrate as described above and a film containing an n-type dopant is grown on top of the p-type ZnO film. In a heteroepitaxial p-n junction the values of the band gap energies of the p-type film and the n-type film are different. The n-type film, may be comprised of a ZnO based material for which the value of the band gap energy has been changed by addition of suitable elements, or the n-type film may be another material such as zinc selenide or gallium nitride.

The use of heteroepitaxial p-n junctions prepared in accordance with the present invention provides additional

materials for p-n junction and device fabrication so as to achieve an expanded range of band gap energies, increased optical tuning ranges, increased device lifetimes, more desirable processing parameters and conditions, as well as
5 other advantages that will be recognized by one skilled in the art.

It will be recognized by one skilled in the art that, similar to the preparing of ZnO films on a substrate, the preparation of homoepitaxial and heteroepitaxial p-n
10 junctions can be accomplished using additional techniques in place of pulsed laser deposition. Other techniques include MBE, MBE with laser ablation, CVD, and MOCVD. It will also be recognized that devices having a more complex structure such as n-p-n transistors, p-n-p transistors,
15 FETs, photodetectors, lattice matching layers, and layers on which electrical leads may be attached can easily be fabricated using the above-described techniques and processes.

In accordance with the present invention, p-type ZnO
20 material may be used as substrate material to reduce or eliminate problems associated with lattice mismatch. p-type ZnO material that has a sufficiently high net acceptor concentration and low electrical resistivity can be used for forming electrical contacts with desirable properties
25 on devices. For example, a template p-type ZnO layer can be synthesized on two-compound semiconductor substrates such as GaAs. This template would provide a transition layer for growing epitaxial GaN-based materials with a density of defects that is lower than would occur in GaN
30 films grown directly on GaAs.

The present invention is illustrated by the following example which is merely for the purpose of illustration and

is not to be regarded as limiting the scope of the invention or manner in which it may be practiced.

EXAMPLE 1

In this example a ZnO film was synthesized on a gallium arsenide substrate and the film/substrate was annealed to diffuse p-type arsenic dopant from the substrate into the film to produce a p-type ZnO film on a gallium arsenide substrate.

A gallium arsenide substrate having the shape of a thin wafer and being about 1 centimeter by about 1 centimeter by about 0.05 centimeters was loaded into a pulsed laser deposition chamber, the temperature of the substrate set at 450°C, and the chamber filled with high purity hydrogen to a pressure of about 2 Torr. An iron shutter was inserted in front of the gallium arsenide substrate to create a separation distance of 4 centimeters between the substrate and the shutter. An argon fluoride excimer pulsed laser beam having an intensity of 50 mJ and a repetition rate of 20 Hz was directed at the metal shutter through a laser window and the shutter was illuminated for about 20 minutes to clean the substrate. Subsequently, the hydrogen was pumped out of the chamber, and the substrate temperature was decreased to about 300°C.

After the substrate was cleaned, the metal shutter was removed and a focusing lens was inserted in front of the laser window to focus the laser beam. The polycrystalline ZnO target was pre-ablated with the excimer pulsed laser beam which was operating at an intensity of about 50 mJ and having a repetition of about 20Hz for a period of about 10 minutes. High purity oxygen gas was then introduced into the chamber to create a pressure of about 35 mTorr.

The excimer pulsed laser beam, operating at an intensity of about 90 mJ and a repetition of about 20 Hz, was then directed at the polycrystalline ZnO for a period of about 2 hours to grow a ZnO film having a thickness of about 1.0 micrometers on the substrate.

After the film growth, the oxygen gas pressure in the chamber was adjusted to about 2 Torr, and the temperature of the substrate is increased to about 500°C. The film/substrate was annealed for about 30 minutes to diffuse arsenic atoms from the substrate into the ZnO film. The annealing created an arsenic doped p-type ZnO film on the gallium arsenide substrate.

Fig. 2 shows a photoluminescence spectra at 20°K of the ZnO film (solid line) and the arsenic-doped ZnO film (dots) prepared in this Example. The pumping excitation is from a pulsed nitrogen laser with a power density of 128 kW/cm². The spectra shows that for the ZnO film the donor-bound excitonic peaks located at about 3.36 eV (3698 angstroms) are dominant. However, the arsenic doped ZnO film of the present example shows that the acceptor-bound excitonic peak located at about 3.32 eV (3742 angstroms) is the strongest peak. This feature of acceptor-bound excitonic peaks indicates that the acceptor density is greatly increased with arsenic doping, and the ZnO film becomes p-type.

Fig. 3 shows a Secondary Ion Mass Spectroscopy (SIMS) plot of the arsenic doped ZnO film prepared in this Example. The plot shows the concentration in atoms/cm³ of arsenic as a function of depth from the surface of the arsenic doped ZnO film. This plot shows that the arsenic concentration is about 10¹⁸ atoms/cm³ to about 10²¹ atoms/cm³ throughout the film.

EXAMPLE 2

In this example a p-n junction, such as the p-n junction shown in Fig. 10, was synthesized utilizing p-type and n-type ZnO material on a zinc doped gallium arsenide substrate. The electrical properties of the p-n junction were measured and electrical data gathered to demonstrate that the device fabricated shows p-n junction behavior.

A zinc doped (0001) gallium arsenide substrate having the shape of a thin wafer and being about 1 centimeter by about 1 centimeter by about 0.05 centimeters was loaded into a pulsed laser deposition chamber. To clean the substrate the temperature was set at 450°C, and the chamber filled with high purity hydrogen gas to create a pressure of about 2 Torr. An iron shutter was inserted in front of the gallium arsenide substrate to create a separation distance of about 4 centimeters between the substrate and the shutter. An argon fluoride excimer pulsed laser beam having an intensity of about 50 mJ and a repetition rate of about 20 Hz was directed at the metal shutter through a laser window (in the absence of a focusing lens) and the shutter was illuminated for about 20 minutes to clean the substrate. Subsequently, the hydrogen was pumped out of the chamber, and the temperature in the chamber was lowered to about 400°C in preparation for film growth.

After the substrate was cleaned, a focusing lens was inserted in front of the laser window to focus the laser beam onto the polycrystalline ZnO target. The polycrystalline ZnO target was pre-ablated with the excimer pulsed laser beam which was operating at an intensity of about 50 mJ and having a repetition of about

20Hz for a period of about 10 minutes. The metal shutter was in place between the target and the substrate to protect the substrate from contamination during pre-ablation. After the pre-ablation was completed, the
5 metal shutter was removed and high purity oxygen was introduced as an ambient gas to create a pressure of about 40 mTorr during p-type film growth.

The excimer pulsed laser beam, operating at an intensity of about 90 mJ and a repetition of about 20Hz,
10 was then directed at the polycrystalline ZnO for a period of about 2 hours to grow a ZnO film having a thickness of about 1.5 micrometers on the substrate. The separation distance between the substrate and the target was about 7 cm. After the laser beam was shut off, the substrate
15 temperature was adjusted to about 450°C and held for 20 minutes in an ambient gas pressure of about 40 mTorr. Finally, the temperature was decreased to about 350°C, and the n-type layer growth steps initiated.

For growth of the n-type layer on top of the p-type
20 layer, the target was replaced with an alloy of ZnO and aluminum oxide (Al_2O_3) wherein the Al_2O_3 was about 2% by atomic weight. The metal shutter was placed between the target and the substrate, the temperature of the substrate adjusted to about 350°C, and the oxygen
25 pressure adjusted to 40 mTorr. The laser was operating at an intensity of 50 mJ and a repetition rate of 20Hz. The target was pre-ablated for a period of 20 minutes.

After pre-ablation, the metal shutter was removed and the laser beam adjusted to an intensity of 90 mJ with
30 a repetition rate of 20Hz and was focused on the alloy target for a period of about 2 hours to grow a film having a thickness of about 1.5 micrometers. The

distance between the target and the substrate was about 7 cm. After growth, the laser beam was shut off and the substrate having the p-type and n-type layer cooled to room temperature.

5 Fig. 6 shows electrical properties of an n-type layer of an aluminum doped ZnO film grown on an undoped GaAs substrate utilizing the same process described for growth of the n-type ZnO layer in Example 2. The data is presented over a range of magnetic fields from 1001 Gauss
10 to 5004 Gauss as shown in the Field column at a temperature of about 290 Kelvin. The Hall Coefficient values are negative values throughout the entire Gauss range indicating that the net carrier concentration is negative and the material is n-type. The resistivity
15 values are low and indicate that the n-type film has electrical conductivity properties sufficient for use in the fabrication of electrical devices. The carrier density values are negative indicating the film is n-type. Also, these values are above 10^{18}cm^{-3} which indicate
20 that the carrier concentration is sufficient for use in electrical devices. Finally, the Mobility values are all negative and near the value of $1\text{cm}^2/\text{volt-sec}$ and indicate the film is n-type and has carrier mobility properties sufficient for fabrication of electrical devices.

25 Fig. 7 shows a current-voltage measurement made on the aluminum doped ZnO film. Fig. 7 shows that the electrical current versus applied voltage approximates a straight line from about 8 volts negative to about 8 volts positive (centered about zero) which demonstrates
30 that the electrical behavior is that of an ohmic material and not a p-n junction device which would display rectifying behavior.

Fig. 8 shows a current-voltage measurement made on an arsenic doped ZnO film grown on zinc doped GaAs substrate using the same process as described for growth of the p-type ZnO layer in Example 1. Fig. 8 shows that the electrical current versus applied voltage approximates a straight line from about 0.6 volts negative to about 0.6 volts positive (centered about zero) which demonstrates that the electrical behavior is that of an ohmic material and not a p-n junction device. It will be recognized by one skilled in the art that for p-type material in contact with p-type material it is sufficient to measure current versus applied voltage in a more restricted range to demonstrate ohmic behavior.

Fig. 9 shows a current-voltage measurement on the entire p-n junction of Example 2. the fact that the electrical current versus applied voltage rises above a straight line for applied voltages greater than 1 volt positive for this device and the fact that the electrical current versus applied voltage approximates a straight line for applied voltages to about 2 volts negative demonstrates that the electrical behavior of the device does not display the behavior of an ohmic material and does display the electrical characteristics of a rectifying device and a p-n junction.

In view of the above, it will be seen that the several objects of the invention are achieved.

As various changes could be made in the above-described process for preparing p-type ZnO films without departing from the scope of the invention, it is intended that all matter contained in the above description be interpreted as illustrative and not in a limiting sense.

WHAT IS CLAIMED IS:

1. A ZnO film on a substrate, the ZnO film containing a p-type dopant and having a net acceptor concentration of at least about 10^{15} acceptors/cm³, a resistivity no greater than about 1 ohm-cm, and a Hall Mobility of between about 0.1 and about 50 cm²/Vs.
5
2. The film as set forth in claim 1 wherein the net acceptor concentration is between about 10^{18} acceptors/cm³ and about 10^{21} acceptors/cm³, the resistivity is between about 1 ohm-cm and about 10^{-4} ohm-cm, and the Hall Mobility is between about 0.1 and about 50 cm²/Vs.
5
3. The film as set forth in claim 1 wherein the net acceptor concentration is at least about 10^{16} acceptors/cm³, the resistivity is between about 1 ohm-cm and about 10^{-4} ohm-cm, and the Hall Mobility is between about 0.1 and about 50 cm²/Vs.
5
4. The film as set forth in claim 1 wherein the p-type ZnO film has a thickness of between about 0.5 and about 3 micrometers.
5. The film as set forth in claim 1 wherein the p-type dopant is arsenic.
6. The film as set forth in claim 1 wherein the substrate is GaAs.
7. The film as set forth in claim 1 wherein the p-type dopant is arsenic and the substrate is GaAs.

8. The film as set forth in claim 1 wherein the p-type dopant is selected from Group 1, 11, 5, and 15 elements.

9. The film as set forth in claim 1 wherein the film is incorporated into a p-n junction.

10. The film as set forth in claim 1 wherein the film is incorporated into a field effect transistor.

11. The film as set forth in claim 1 wherein the film is incorporated into a light emitting diode.

12. The film as set forth in claim 1 wherein the film is incorporated into a laser diode.

13. The film as set forth in claim 1 wherein the film is incorporated into a photodetector diode.

14. The film as set forth in claim 1 wherein the film is incorporated into a device as a substrate material for lattice matching to materials in the device.

15. The film as set forth in claim 2 wherein the p-type ZnO film has a thickness of between about 0.5 and about 3 micrometers.

16. The film as set forth in claim 2 wherein the p-type dopant is arsenic.

17. The film as set forth in claim 2 wherein the substrate is GaAs.

18. The film as set forth in claim 2 wherein the p-type dopant is arsenic and the substrate is GaAs.

19. The film as set forth in claim 2 wherein the p-type dopant is selected from Group 1, 11, 5, and 15 elements.

20. The film as set forth in claim 2 wherein the film is incorporated into a p-n junction.

21. The film as set forth in claim 2 wherein the film is incorporated into a field effect transistor.

22. The film as set forth in claim 2 wherein the film is incorporated into a light emitting diode.

23. The film as set forth in claim 2 wherein the film is incorporated into a laser diode.

24. The film as set forth in claim 2 wherein the film is incorporated into a photodetector diode.

25. The film as set forth in claim 2 wherein the film is incorporated into a device as a substrate material for lattice matching to materials in the device.

26. A process for growing a p-type ZnO film containing arsenic on a GaAs substrate in a pulsed laser deposition chamber, the process comprising:

- cleaning the GaAs substrate;
- 5 adjusting the temperature of the substrate in the pulsed laser deposition chamber to between about 300°C to about 450°C;
- pre-ablating a polycrystalline ZnO crystal;
- directing an excimer pulsed laser beam onto the
- 10 polycrystalline ZnO crystal to grow a film on the GaAs substrate;
- increasing the temperature of the substrate in the pulsed laser deposition chamber to between about 450°C and about 600°C; and
- 15 annealing the ZnO coated GaAs substrate to diffuse at least about 1×10^{15} acceptors/cm³ from the GaAs into the ZnO film to produce an arsenic doped ZnO film.

27. The process as set forth in claim 26 wherein the ZnO film has a thickness of between about 0.5 and about 3 micrometers.

28. The process as set forth in claim 26 wherein the arsenic doped ZnO film has a net acceptor concentration of between about 1×10^{18} acceptors/cm³ and about 1×10^{21} acceptors/cm³, a resistivity of between about 1 and about 1×10^{-4} ohm-cm, and a Hall Mobility of between about 0.1 and about 50 cm²/Vs.

29. The process as set forth in claim 26 wherein the arsenic doped ZnO film has a net acceptor concentration of at least about 1×10^{16} acceptors/cm³, a resistivity of between about 1 and about 1×10^{-4} ohm-cm, and a Hall Mobility of between about 0.1 and about 50 cm²/Vs.

30. The process as set forth in claim 26 wherein the substrate is cleaned in the pulsed laser deposition chamber using a pulsed excimer laser.

31. The process for growing a p-type ZnO film on a substrate, the process comprising:

cleaning the substrate;

adjusting the temperature in the pulsed laser
5 deposition chamber to between about 200°C and about
1000°C; and

growing a p-type ZnO film on the substrate by
directing an excimer pulsed laser beam onto a pressed ZnO
powder pellet containing a p-type dopant to grow a p-type
10 ZnO film containing at least about 10^{15} acceptors/cm³ on
the substrate.

32. The process as set forth in claim 31 wherein the temperature in the pulsed laser deposition chamber is adjusted to between about 300°C and about 450°C.

33. The process as set forth in claim 31 wherein the p-type ZnO film has a thickness of between about 0.5 and about 3 micrometers.

34. The process as set forth in claim 31 wherein the p-type dopant is selected from group 1, 11, 5, and 15 elements.

35. The process as set forth in claim 31 wherein the p-type ZnO film has a net acceptor concentration of between about 10^{18} acceptors/cm³ and about 10^{21}

acceptors/cm³, a resistivity no greater than about 1
5 ohm-cm, and a Hall Mobility of between about 0.1 and
about 50 cm²/Vs.

36. The process as set forth in claim 31 wherein
the p-type ZnO film has a net acceptor concentration of
at least about 10¹⁶ acceptors/cm³, a resistivity no
greater than about 1 ohm-cm, and a Hall Mobility of
5 between about 0.1 and about 50 cm²/Vs.

37. The process as set forth in claim 31 wherein
the p-type dopant is arsenic.

38. The process as set forth in claim 31 wherein
the substrate is cleaned in the pulsed laser deposition
chamber using a pulsed excimer laser.

39. A process for preparing a p-n junction having a
p-type ZnO film and an n-type film wherein the net
acceptor concentration is at least about 10¹⁵
acceptors/cm³, the process comprising:

5 cleaning a substrate;

adjusting the temperature of the substrate in the
pulsed laser deposition chamber to between about 200°C to
about 1000°C;

growing a p-type ZnO film on the substrate by
10 directing an excimer pulsed laser beam onto a pressed ZnO
powder pellet containing a p-type dopant element to grow
a p-type ZnO film containing at least about 10¹⁸
acceptors/cm³ on the substrate; and

growing an n-type film on top of the p-type ZnO film
15 by directing an excimer pulsed laser beam onto a pressed

powder pellet containing an n-type dopant element to grow an n-type film on the p-type ZnO film on the substrate.

40. The process as set forth in claim 39 wherein the n-type film has a thickness of between about 0.5 and about 3 micrometers and the p-type film has a thickness of between about 0.5 and about 3 micrometers.

41. The process as set forth in claim 39 wherein the p-type dopant element is arsenic and the n-type dopant element is aluminum.

42. The process as set forth in claim 39 wherein the p-n junction is a homoepitaxial p-n junction wherein the p-type film consists of arsenic and ZnO and the n-type film consists of an n-type dopant element and ZnO.

43. The process as set forth in claim 39 wherein the p-n junction is a heteroepitaxial p-n junction wherein the p-type film consists of arsenic and ZnO and the n-type film contains an n-type dopant and has an
5 energy band gap different than ZnO.

44. The process as set forth in claim 39 wherein the substrate is cleaned in the pulsed laser deposition chamber using a pulsed excimer laser.

45. The process as set forth in claim 39 wherein the net acceptor concentration is at least about 10^{16} acceptors/cm³.

46. A process for preparing a p-n junction having a p-type ZnO film and an n-type film wherein the net acceptor concentration is at least about 10^{15} acceptors/cm³, the process comprising:

5 cleaning a substrate;

 adjusting the temperature in the pulsed laser deposition chamber to between about 200°C to about 1000°C;

 growing an n-type film on top of the substrate by directing an excimer pulsed laser beam onto a pressed powder pellet containing an n-type dopant element to grow
10 an n-type film on the substrate;

 growing a p-type ZnO film on the n-type film by directing an excimer pulsed laser beam onto a pressed ZnO powder pellet containing a p-type dopant element to grow
15 a p-type ZnO film containing at least about 10^{18} acceptors/cm³ on the n-type film.

47. The process as set forth in claim 46 wherein the n-type film has a thickness of between about 0.5 and about 3 micrometers and the p-type film has a thickness of between about 0.5 and about 3 micrometers.

48. The process as set forth in claim 46 wherein the p-type dopant element is arsenic and the n-type dopant element is aluminum.

49. The process as set forth in claim 46 wherein the p-n junction is a homoepitaxial p-n junction wherein the p-type film consists of arsenic and ZnO and the n-type film consists of an n-type dopant element and ZnO.

50. The process as set forth in claim 46 wherein the p-n junction is a heteroepitaxial p-n junction wherein the p-type film consists of arsenic and ZnO and the n-type film contains an n-type dopant and has an energy band gap different than ZnO.

51. The process as set forth in claim 46 wherein the substrate is cleaned in the pulsed laser deposition chamber using a pulsed excimer laser.

52. The process as set forth in claim 46 wherein the net acceptor concentration is at least about 10^{16} acceptors/cm³.

53. A process for cleaning a substrate in a chamber prior to growing a film on the substrate, the process comprising:

loading the substrate into the chamber and adjusting the temperature in the chamber to between about 400°C and about 500°C;

filling the chamber with hydrogen to create a pressure in the chamber of between about 0.5 and about 3 Torr;

adjusting the distance between a metal shutter in the chamber and the substrate to between about 3 to about 6 centimeters; and

directing an excimer pulsed laser beam having an intensity of between about 20 to about 70 mJ and a repetition of between about 10 to about 30 Hz into the chamber for a period of between about 5 and about 30 minutes to illuminate the metal shutter and clean the substrate.

54. The process as set forth in claim 53 wherein the chamber temperature is about 450°C, the metal shutter is about 4 centimeters from the substrate, and an argon fluoride pulsed excimer laser having an intensity of about 50 mJ and a repetition of about 20 Hz illuminates the shutter for about 20 minutes to clean the substrate.

55. A p-type film on a substrate wherein the film contains a p-type dopant which is an element which is the same as an element which is a constituent of the substrate.

56. The p-type film as set forth in claim 55 wherein the p-type film comprises ZnO, the substrate comprises GaAs, and the element which is the p-type dopant and a constituent of the substrate is arsenic.

57. A process for preparing a p-n junction having a p-type ZnO film and an n-type ZnO film on a p-type doped substrate wherein the net acceptor concentration of the substrate and p-type ZnO film is at least about 10^{15} acceptors/cm³, the process comprising:

adjusting the temperature of the substrate in a pulsed laser deposition chamber to between about 200 and about 1000°C;

growing a p-type ZnO film on the p-type doped substrate by directing an excimer pulsed laser beam onto a pressed ZnO powder pellet containing a p-type dopant element to grow a p-type ZnO film containing at least about 10^{15} acceptors/cm³ on the p-type doped substrate; and

15 growing an n-type film on top of the p-type ZnO film by directing an excimer pulsed laser beam onto a pressed powder pellet containing an n-type dopant element to grow an n-type film on the p-type ZnO film on the p-type substrate.

58. The process as set forth in claim 57 wherein the substrate is cleaned prior to growing the p-type and n-type films.

59. The process as set forth in claim 57 wherein the p-type dopant element of the film is arsenic, the n-type dopant element is aluminum, the substrate is GaAs, and the p-type dopant element of the substrate is zinc.

60. The process as set forth in claim 57 wherein the p-n junction is a homoepitaxial p-n junction wherein the p-type film consists of arsenic and ZnO and the n-type film consists of an n-type dopant element and ZnO.

61. The process as set forth in claim 57 wherein the p-n junction is a heteroepitaxial p-n junction wherein the p-type film consists of arsenic and ZnO and the n-type film contains an n-type dopant and has an
5 energy band gap different than ZnO.

62. The process as set forth in claim 57 wherein the temperature of the substrate in the laser deposition chamber is adjusted to between about 400°C and about 450°C and the p-type ZnO film is grown on the p-type doped
5 substrate by directing an excimer pulsed laser beam onto a pressed ZnO powder pellet.

63. A process for growing a doped ZnO film on a substrate, the process comprising:

adjusting the temperature of the substrate in a pulsed laser deposition chamber to between about 200°C and
5 about 1000°C;

preablating a polycrystalline ZnO crystal target;
and

directing the excimer pulsed laser beam onto the polycrystalline ZnO crystal target to grow a film on the
10 GaAs substrate while simultaneously directing a molecular beam containing a dopant onto the growing ZnO film for a time sufficient to incorporate at least about 10^{15} dopant/cm³.


64. The process as set forth in claim 63 wherein a p-type ZnO film is grown on the substrate using a arsenic molecular beam wherein the p-type dopant is selected from the group consisting of Group 1, Group 11, Group 5, and
5 Group 15 elements.

65. The process as set forth in claim 63 wherein an n-type ZnO film is grown on the substrate using a molecular beam wherein the n-type dopant is selected from the group consisting of aluminum, gallium, and indium.

66. The process as set forth in claim 63 wherein two doped ZnO films are grown on a substrate to form a p-n junction, the first doped ZnO film being p-type and being grown on the substrate and the second ZnO film
5 being n-type and being grown on top of the p-type film.

67. The process as set forth in claim 63 wherein two doped ZnO films are grown on a substrate to form a p-n junction, the first doped ZnO film being n-type and being grown on the substrate and the second ZnO film
5 being p-type and being grown on top of the n-type film.

FIG. 1



2/10

PL: ZnO VS p-ZnO:As at 20 K




Fig. 3

3/10

SIMS: p-ZnO


Primary Ion Beam: Cs⁺

Fig. 4

4/10

0.5 μ m




Fig 5

5/10

0.5 μ m




Fig. 6
Table I. Electrical properties of Al-doped ZnO on Al₂O₃ measured by the Van der Pauw method. The column headings are, respectively from left to right, magnetic field in units of Gauss, Hall coefficient in units of cm³/Coulomb, resistivity in units of Ohm-cm, density of carriers in units of cm⁻³, carrier mobility in units of cm²/volt-sec, and sample temperature in units of Kelvin.

Field (Gauss)	Hall Coefficient (cm ³ /Coulomb)	Resistivity (Ohm-cm)	Carrier Density (cm ⁻³)	Mobility (cm ² /volt-sec)	Temperature (Kelvin)
5004	-1.13	1.03	-5.52 x 10 ¹⁸	-1.09	290
4002	-1.07	1.03	-5.81 x 10 ¹⁸	-1.04	290
3001	-1.13	1.03	-5.53 x 10 ¹⁸	-1.09	290
1998	-1.32	1.03	-4.74 x 10 ¹⁸	-1.27	290
1001	-1.50	1.03	-4.16 x 10 ¹⁸	-1.45	290


Fig. 7

7/10

Current (mA)

Al - doped ZnO

I - V Measurement



Voltage (V)

8/10

Current (mA)

Fig. 8

I - V Measurement

ZnO:As on GaAs:Zn





Fig. 9


I - V Measurement

PN - Junction of ZnO

10/10

A CROSS SECTION OF A ZnO P-N JUNCTION

Fig 10



INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 99/17486

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 H01L33/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 H01L

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	<p>MINESGISHI K ET AL: "GROWTH OF P-TYPE ZINC OXIDE FILMS BY CHEMICAL VAPOR DEPOSITION"</p> <p>JAPANESE JOURNAL OF APPLIED PHYSICS, JP, PUBLICATION OFFICE JAPANESE JOURNAL OF APPLIED PHYSICS. TOKYO, vol. 36, no. 11A, page L1453-L1455</p> <p>XP000834594</p> <p>ISSN: 0021-4922</p> <p>cited in the application</p> <p>the whole document</p> <p style="text-align: center;">---</p> <p style="text-align: center;">-/--</p>	1

☒ Further documents are listed in the continuation of box C.

☐ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"Z" document member of the same patent family

Date of the actual completion of the international search

30 November 1999

Date of mailing of the international search report

06/12/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

De Laere, A

INTERNATIONAL SEARCH REPORT

Inter. nal Application No

PCT/US 99/17486

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	CRACIUN V ET AL: "Growth of ZnO thin films on GaAs by pulsed laser deposition" THIN SOLID FILMS, CH, ELSEVIER-SEQUOIA S.A. LAUSANNE, vol. 259, no. 1, page 1-4 XP004004743 ISSN: 0040-6090 the whole document	1,26
A	HIRAMATSU M ET AL: "Transparent conducting ZnO thin films prepared by XeCl excimer laser ablation" EIGHTH CANADIAN SEMICONDUCTOR TECHNOLOGY CONFERENCE, vol. 16, no. 2, pages 669-673, XP000856168 Journal of Vacuum Science & Technology A (Vacuum, Surfaces, and Films), March-April 1998, AIP for American Vacuum Soc, USA ISSN: 0734-2101 cited in the application abstract	1,26

THIS PAGE BLANK (USPTO)